

CLAIMS

1. A thermal print head comprising:

an insulating board;

5 a glaze layer formed on the board;

a wiring pattern formed on the glaze layer; and

an electrode connected to the wiring pattern,

wherein the electrode includes a pad provided on the wiring pattern and an upper layer formed on the pad, the upper layer having a higher solderability than the pad while having a smaller area than the pad.

10

2. The thermal print head according to claim 1, wherein the upper layer has a selected dimension which is no greater than 0.75 times a corresponding dimension of the pad.

15

3. The thermal print head according to claim 1, wherein a joint surface area between the pad and the upper layer is no greater than 0.75^2 times an upper surface area of the pad.

20

4. The thermal print head according to claim 1, wherein the pad is made of Ag, the upper layer being made of a material selected from the group comprising Ag containing a solderability-improving additive, Ag-Pt and Ag-Pd.

25

5. The thermal print head according to claim 4, wherein the additive is bismuth oxide.

6. The thermal print head according to claim 1, wherein the pad includes a corner having a contained angle of larger than 90° as viewed in plan for preventing stress concentration.
- 5 7. The thermal print head according to claim 1, further comprising a pin contacting the electrode for external connection, the pin being soldered to the upper layer.